

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 028 130 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
16.08.2000 Bulletin 2000/33

(51) Int. Cl.⁷: **C08F 236/20**, **C08F 232/08**,
C08L 21/00

(21) Application number: 00101855.5

(22) Date of filing: 31.01.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 09.02.1999 US 246391

(71) Applicant:
THE GOODYEAR TIRE & RUBBER COMPANY
Akron, Ohio 44316-0001 (US)

(72) Inventors:
• Wideman, Lawson Gibson
Hudson, Ohio 44236 (US)
• Segatta, Thomas Joseph
Copley, Ohio 44321 (US)
• Keith, Denise Jeannette
Akron, Ohio 44306 (US)

(74) Representative: Leitz, Paul
Goodyear Technical Center-Luxembourg
Patent-Department
L-7750 Colmar-Berg (LU)

(54) **Polymeric dicyclopentadiene/limonene resin**

(57) This invention relates to a novel class of polymeric resins which have a softening point ranging from 50°C to 220°C and a molecular weight ranging from 500 to 42,000 g/mol. The resins consist essentially of the polymers which result from the polymerization reaction between dicyclopentadiene and limonene. The polymeric resins are particularly useful in improving traction of the rubber when used in tire treads.

EP 1 028 130 A1

Description

Background of the Invention

- 5 [0001] This invention relates to a polymeric resin which is the reaction product of the polymerization reaction between dicyclopentadiene and limonene. Use of the polymeric resins of the present invention in a rubber tire stock improves the traction and handling of the tire.

Summary of the Invention

- 10 [0002] The present invention relates to a polymeric dicyclopentadiene/limonene resin. The polymeric resins of the present invention have softening points ranging from 50°C to 220°C, and a molecular weight of from 500 to 42,000. The present invention also includes a blend of dicyclopentadiene/limonene resins and rubber stocks containing the dicyclopentadiene/limonene resin.

Detailed Description of the Invention

- 15 [0003] The present invention relates to a polymeric resin consisting essentially of the reaction product of the polymerization reaction between dicyclopentadiene and limonene and having a softening point ranging from 50°C to 220°C and a molecular weight ranging from 500 to 42,000.

[0004] In addition, the present invention relates to a resin composition comprising a blend of two or more polymeric resins wherein each resin consists essentially of the reaction product of the polymerization reaction between dicyclopentadiene and limonene. Alternatively, the blend can be formed in-situ; that is, the reaction temperature may be raised during the polymerization to increase the molecular weight distribution and broaden the softening point.

- 25 [0005] In addition, there is disclosed a pneumatic tire having a tread comprised of a rubber stock comprising (1) a rubber selected from the group consisting of natural rubber, rubber derived from a diene monomer or mixtures thereof, and (2) a polymeric resin composition consisting essentially of the reaction product of the polymerization reaction between dicyclopentadiene and limonene; said resin having a softening point ranging from 50 to 220°C and a molecular weight ranging from 500 to 42,000.

- 30 [0006] There is also disclosed a rubber stock comprising (1) a rubber selected from the group consisting of natural rubber, rubber derived from a diene monomer or mixtures thereof, and (2) a polymeric resin composition consisting essentially of the reaction product of the polymerization reaction between dicyclopentadiene and limonene; said resin having a softening point ranging from 50 to 220°C and a molecular weight ranging from 500 to 42,000.

- 35 [0007] The terms "polymeric compound" and "polymer" when used to describe the resins of the present invention are intended to only include those molecules which contain a monomeric unit derived from dicyclopentadiene and limonene and where at least one of the monomeric units derived from the dicyclopentadiene or limonene is repeated. Therefore, the compounds formed by the reaction of a single dicyclopentadiene molecule and a single limonene are not polymeric as the term is used herein. The term monomeric unit means a structure that occurs in a polymeric compound and which differs from the structure of dicyclopentadiene or limonene due to changes resulting from molecular reorientation during the linking to the adjacent structure. These changes may include addition to a double bond or the addition or removal of a hydrogen atom from the dicyclopentadiene or limonene.

- 40 [0008] The molar ratio of the dicyclopentadiene to limonene in the polymerization reaction may vary, depending on the desired properties of the final polymeric product. For example, the molar ratio of the dicyclopentadiene to limonene as starting material may range from 1:10 to 10:1. The preferred molar ratio of dicyclopentadiene to limonene may range from 5:1 to 1:5 as starting material. The most preferred ratio ranges from 2:1 to 1:2. As to the final product, the molar ratio of polymeric units derived from the dicyclopentadiene to limonene may range from 8:1 to 1:8. The preferred molar ratio of dicyclopentadiene to limonene in the final product ranges from 1:3 to 3:1 with a range of from 2.1:1 to 1:2.1, being particularly preferred.

- 45 [0009] The polymerization reaction between the dicyclopentadiene may be a thermal (no catalyst) polymerization, or catalyzed, i.e., conducted in the presence of an acid catalyst. Examples of acid catalysts that may be used include Bronsted acid and Lewis acid-type catalysts. Such known acid catalysts include H₂SO₄, HCl, H₃PO₄, metal halides such as BF₃, BCl₃, AlCl₃, AlBr₃, SnCl₄, ZnCl₂, SbCl₃ and their etherates. The choice of a particular catalyst is dependent upon factors including the melting or boiling points of the reactants, desired rate of reaction, solvent, and pressure and temperature limitation of the production equipment, etc. When higher yields are desired, the metal halides or their etherates may be utilized. The preferred acid catalysts are BF₃ and AlCl₃. The most preferred catalyst is AlCl₃.

- 55 [0010] In the catalyzed polymerization process, the amount of catalyst may range from 0.1 to 20 weight percent of catalyst based on the total weight of reactants to be polymerized. Preferably, a range of from 3 to 5 weight percent of catalyst is preferred. The optimum concentration of catalyst depends on the nature of the solvent, if any, which effects

the solubility of the catalyst as well as on the stirring efficiency inside the polymerization reactor. High catalyst concentration reduces the resin molecular weight distribution and, therefore, limits the amount of feed additive required for controlling the resin molecular weight.

[0011] The polymerization reaction may be carried out neat (without solvent) at or above the melting points of the reactants, or can be carried out in the presence of a solvent. The solvent may be an aliphatic C₆-C₁₂ hydrocarbon, an aromatic or haloaromatic (C₆-C₉) hydrocarbon, or a C₆-C₉ aliphatic halohydrocarbon. Examples of suitable solvents include hexane, heptane, cyclohexane, benzene, toluene, xylene, and chlorobenzene. The preferred solvents are hexane and cyclohexane.

[0012] The polymerization reaction may be conducted under a variety of operating conditions. The reaction pressure may vary and range from one atmosphere to 100 atmospheres with a pressure of from two atmospheres to ten atmospheres being preferred. The reaction temperature may range from 0 to 100 °C with a preferred range being from 30 to 50°C.

[0013] Depending on the reactivity of the reactants, amount of catalyst, reaction pressure and reaction temperature, the reaction time may vary. *Generally speaking, the reaction time varies from 1 to 8 hours.*

[0014] The molecular weight distribution of the polymeric resin of the present invention may range from 500 to 42,000. In a particularly preferred embodiment of the present invention, the resin composition comprises a blend of two or more individual polymeric resins each one of which is the reaction product of a polymerization reaction between dicyclopentadiene and limonene. Each individual polymeric resin preferably differs from the other by having a different molecular weight range. Generally speaking, all of the polymeric resins will exhibit some lower molecular weight values, however, not all of the individual resins may include the higher molecular values. In the alternative, all of the resins may have distributions that vary by their lower molecular values with the high molecular weight value relatively being the same. For example, when the resin blend comprises three individual polymeric resins, the first resin may have a molecular weight ranging from 700 to 24,000, the second resin may have a molecular weight ranging from 700 to 36,000, and the third resin may have a molecular weight ranging from 700 to 42,000.

[0015] In accordance to another embodiment of the present invention, the resin composition may comprise a blend of four individual resins. In accordance with this embodiment, the first resin may have a molecular weight ranging from 500 to 15,000, the second resin may have a molecular weight ranging from 700 to 15,000, the third resin may have a molecular weight ranging from 3,000 to 15,000, and the fourth resin may have a molecular weight ranging from 4,000 to 15,000.

[0016] The blend may be formed in-situ or mechanically blended.

[0017] The resin composition of the present invention has a softening point ranging from 50 to 220. For the purposes of the present invention, the term "softening point" is used to describe the temperature range from when wetting occurs in a capillary melting point tube to where the resin is completely liquid. Representative of suitable equipment to determine the relative softening point is a Thomas-Hoover Melting Point apparatus equipped with a silicon oil bath. In accordance with the embodiment of the present invention when the resin composition comprises a blend of three individual resins, the first resin may have a softening point ranging from 134 to 156°C, the second resin may have a softening point ranging from 138 to 180°C, and the third resin may have a softening point ranging from 188 to 208°C. In accordance with the embodiment of the present invention where the blend comprises four individual resins, the first resin may have a softening point ranging from 55 to 75°C, the second resin may have a softening point ranging from 80 to 131°C, the third resin may have a softening point ranging from 126 to 168°C, and the fourth resin may have a softening point range of 168 to 195°C.

[0018] Rubber stocks containing natural rubber or rubbers derived from a diene monomer may be modified with the resin compositions of the present invention. Examples of rubbers derived from a diene monomer include substituted and unsubstituted, saturated and unsaturated, synthetic polymers. The natural polymers include natural rubber in its various forms, e.g., pale crepe and smoked sheet, and balata and gutta percha. The synthetic polymers include those prepared from a single monomer (homopolymer) or a mixture of two or more copolymerizable monomers (copolymer) when the monomers are combined in the random distribution or block form. In addition to the diene monomers, other monomers may be used. Of all the monomers that may be used, the monomers may be substituted or unsubstituted and may possess one or more double bonds, for example, diene monomers, both conjugated and nonconjugated, and monoolefins, including cyclic and acyclic monoolefins, especially vinyl and vinylidene monomers. Examples of conjugated dienes are 1,3-butadiene, isoprene, chloroprene, 2-ethyl-1,3-butadiene, 2,3-dimethyl-1,3-butadiene and piperylene. Examples of nonconjugated dienes are 1,4-pentadiene, 1,4-hexadiene, 1,5-hexadiene, dicyclopentadiene, 1,5-cyclooctadiene and ethylidene norbornene. Examples of acyclic monoolefins are ethylene, propylene, 1-butene, isobutylene, 1-pentene and 1-hexene. Examples of cyclic monoolefins are cyclopentene, cyclohexene, cycloheptene, cyclooctene and 4-methyl-cyclooctene. Examples of vinyl monomers are styrene, acrylonitrile, acrylic acid, ethylacrylate, vinyl chloride, butylacrylate, methyl vinyl ether, vinyl acetate and vinyl pyridine. Examples of vinylidene monomers are alpha-methylstyrene, methacrylic acid, methyl methacrylate, itaconic acid, ethyl methacrylate, glycidyl methacrylate and vinylidene chloride. Representative examples of the synthetic polymers used in the practice of this invention are

polychloroprene, homopolymers of a conjugated 1,3-diene such as isoprene and butadiene, and in particular, polyisoprenes and polybutadienes having essentially all of their repeat units combined in a cis-1,4-structure; and copolymers of a conjugated 1,3-diene such as isoprene and butadiene with up to 50 percent by weight of at least one copolymerizable monomer, including ethylenically unsaturated monomers such as styrene or acrylonitrile; and butyl rubber, which is a polymerization product of a major proportion of a monoolefin and a minor proportion of a diolefin such as butadiene or isoprene.

[0019] The rubber compounds which may be modified by the resins of the present invention are preferably cis-1,4-polyisoprene (natural or synthetic), polybutadiene, polychloroprene and the copolymers of isoprene and butadiene, copolymers of acrylonitrile and butadiene, copolymers of acrylonitrile and isoprene, copolymers of styrene, butadiene and isoprene, copolymers of styrene and butadiene and blends thereof.

[0020] The amount of polymeric resins that may be used with the diene containing polymers may vary and depend on the polymer to be modified, the particular polymeric resin, the desired degree of modification and the like. Generally speaking, the polymeric resin is used in amounts ranging from 5 to 50 parts per hundred (phr) of diene polymer. Preferably, the polymeric resin is used in amounts of from 5 to 25 phr, with a range of from 10 to 25 phr being particularly preferred.

[0021] The polymeric resins may be incorporated in the diene containing polymer by conventional mixing procedures, for example, by adding them in a banbury mixer or by adding them to the rubber on a mill. Preferably, when the polymeric resins have higher molecular weights, it is recommended that they be ground to a fine powder to insure adequate dispersion. Such powders may be treated to suppress dust, for example, by the addition of oil, or they can be mixed with a binder, for example, a polymer latex, and granules or pellets containing up to 5 percent by weight of a binder. They can also be formulated as pre-dispersions or masterbatched in a diene rubber stock, which pre-dispersions may contain, for example, from 15 to 50 percent by weight of the polymeric resin.

[0022] Similar to vulcanizing conventional rubber stocks, the rubber stocks containing the polymeric resins need a sulfur vulcanizing agent. Examples of suitable sulfur vulcanizing agents include elemental sulfur (free sulfur) or sulfur donating vulcanizing agents, for example, an amine disulfide, polymeric polysulfide or sulfur olefin adducts. Preferably, the sulfur vulcanizing agent is elemental sulfur. The amount of sulfur vulcanizing agent will vary depending on the components of the rubber stock and the particular type of sulfur vulcanizing agent that is used. Generally speaking, the amount of sulfur vulcanizing agent ranges from 0.1 to 8 phr with a range of from 1.5 to 6 being preferred.

[0023] Conventional rubber additives may be incorporated in the rubber stock of the present invention. The presence of a sulfur vulcanizing agent and conventional additives are not considered to be an aspect of this invention. The additives commonly used in rubber stocks include fillers, plasticizers, curatives, processing oils, retarders, antioxidants, antioxidants and the like. The total amount of filler that may be used may range from 45 to 130 phr being preferred. Fillers include silicas, clays, calcium carbonate, calcium silicate, titanium dioxide and carbon black. Preferably, at least a portion of the filler is carbon black. Plasticizers, oils or mixtures thereof are conventionally used in amounts ranging from 2 to 150 phr with a range of 5 to 130 phr being preferred. The amount of plasticizer used will depend upon the softening effect desired. Examples of suitable plasticizers include aromatic extract oils, petroleum softeners including asphaltenes, saturated and unsaturated hydrocarbons and nitrogen bases, coal tar products, cumarone-indene resins and esters such as dibutylphthalate and tricresyl phosphate. Examples of oils are commonly known as highly aromatic process oil, process soybean oil and highly paraffinic process oil. Materials used in compounding which function as an accelerator-activator includes metal oxides such as zinc oxide, magnesium oxide and litharge which are used in conjunction with acidic materials such as fatty acid, for example, stearic acid, oleic acid, murastic acid, and the like. The amount of the metal oxide may range from 1 to 10 phr with a range of from 2 to 8 phr being preferred. The amount of fatty acid which may be used may range from 0.25 phr to 5.0 phr with a range of from 0.5 phr to 2 phr being preferred.

[0024] Accelerators may be used to control the time and/or temperature required for vulcanization of the rubber stock. As known to those skilled in the art, a single accelerator may be used which is present in amounts ranging from 0.2 to 3.0 phr. In the alternative, combinations of two or more accelerators may be used which consist of a primary accelerator which is generally used in a larger amount (0.3 to 3.0 phr), and a secondary accelerator which is generally used in smaller amounts (0.05 to 1.50 phr) in order to activate and improve the properties of the rubber stock. Combinations of these accelerators have been known to produce synergistic effects on the final properties and are somewhat better than those produced by use of either accelerator alone. Delayed action accelerators also are known to be used which are not affected by normal processing temperatures and produce satisfactory cures at ordinary vulcanization temperatures. Suitable types of accelerators include amines, disulfides, guanidines, thioureas, thiazoles, thiurams, sulfenamides, dithiocarbamates and the xanthates. Examples of specific compounds which are suitable include zinc diethyldithiocarbamate, 4,4'-dithiodimorpholine, N,N-di-methyl-S-tert-butylsulfenyldithiocarbamate, tetramethylthiuram disulfide, 2,2'-dibenzothiazyl disulfide, butyraldehydeaniline mercaptobenzothiazole, N-oxydiethylene-2-benzothiazolesulfenamide. Preferably, the accelerator is a sulfenamide.

[0025] A class of compounding materials known as scorch retarders are commonly used. Phthalic anhydride, salicylic acid, sodium acetate and N-cyclohexyl thiophthalimide are known retarders. Retarders are generally used in an

amount ranging from 0.1 to 0.5 phr.

[0026] Preformed phenol-formaldehyde type resins may be used in the rubber stock and are generally present in an amount ranging from 1.0 to 5.0 phr, with a range of from 1.5 to 3.5 phr being preferred.

[0027] Conventionally, antioxidants and some times antiozonants, hereinafter referred to as antidegradants, are added to rubber stocks. Representative antidegradants include monophenols, bisphenols, thiobisphenols, polyphenols, hydroquinone derivatives, phosphites, thioesters, naphthyl amines, diphenyl-p-phenylenediamines, diphenylamines and other diaryl amine derivatives, paraphenylenediamines, quinolines and mixtures thereof. Specific examples of such antidegradants are disclosed in The Vanderbilt Rubber Handbook (1990), pages 282-286. Antidegradants are generally used in amounts from 0.25 to 5.0 phr with a range of from 1.0 to 3.0 phr being preferred.

[0028] The mixing of the rubber composition can be accomplished by methods known to those having skill in the rubber mixing art. For example, the ingredients are typically mixed in at least two stages; namely, at least one non-productive stage followed by a productive mix stage. The final curatives including sulfur vulcanizing agents are typically mixed in the final stage which is conventionally called the "productive" mix stage in which the mixing typically occurs at a temperature, or ultimate temperature, lower than the mix temperature(s) than the preceding non-productive mix stage(s). The rubber and polymeric resin are mixed in one or more non-productive mix stages. The terms "non-productive" and "productive" mix stages are well known to those having skill in the rubber mixing art.

[0029] Vulcanization of the pneumatic tire of the present invention is generally carried out at conventional temperatures ranging from 100°C to 200°C. Preferably, the vulcanization is conducted at temperatures ranging from 110°C to 180°C. Any of the usual vulcanization processes may be used such as heating in a press or mold, heating with superheated steam or hot air or in a salt bath.

[0030] The following examples are presented in order to illustrate but not limit the present invention.

[0031] Cure properties were determined using a Monsanto oscillating disc rheometer which was operated at a temperature of 150°C and at a frequency of 11 hertz. A description of oscillating disc rheometers can be found in the Vanderbilt Rubber Handbook edited by Robert O. Ohm (Norwalk, Conn., R. T. Vanderbilt Company, Inc., 1990), pages 554-557. The use of this cure meter and standardized values read from the curve are specified in ASTM D-2084. A typical cure curve obtained on an oscillating disc rheometer is shown on page 555 of the 1990 edition of the Vanderbilt Rubber Handbook.

[0032] In such an oscillating disc rheometer, compounded rubber samples are subjected to an oscillating shearing action of constant amplitude. The torque of the oscillating disc embedded in the stock that is being tested that is required to oscillate the rotor at the vulcanization temperature is measured. The values obtained using this cure test are very significant since changes in the rubber or the compounding recipe are very readily detected. It is obvious that it is normally advantageous to have a fast cure rate.

[0033] In the following examples, the Flexsys Rubber Process Analyzer (RPA) 2000 was used to determine dynamic mechanical rheological properties. The curing conditions were 160°C, 1.667 Hz, 15.8 minutes and 0.7 percent strain. A description of the RPA 2000, its capability, sample preparation, tests and subtests can be found in these references. H A Pawlowski and J S Dick, Rubber World, June 1992; J S Dick and H A Pawlowski, Rubber World, January 1997; and J S Dick and J A Pawlowski, Rubber & Plastics News, April 26 and May 10, 1993.

[0034] The compounded rubber sample is placed on the bottom die. When the dies are brought together, the sample is in a pressurized cavity where it will be subjected to a sinusoidal oscillating shearing action of the bottom die. A torque transducer connected to the upper die measures the amount of torque transmitted through the sample as a result of the oscillations. Torque is translated into the shear modulus, G, by correcting for the die form factor and the strain. The RPA 2000 is capable of testing uncured or cured rubber with a high degree of repeatability and reproducibility. The tests and subtests available include frequency sweeps at constant temperature and strain, curing at constant temperature and frequency, strain sweeps at constant temperature and frequency and temperature sweeps at constant strain and frequency. The accuracy and precision of the instrument allows reproducible detection of changes in the compounded sample.

[0035] The values reported for the storage modulus, (G'), loss compliance (J'') and tan delta are obtained from a strain sweep at 100°C and 1 Hz following the cure test. These properties represent the viscoelastic response of a test sample to shear deformation at a constant temperature and frequency.

[0036] The following examples are presented for the purposes of illustrating and not limiting the present invention. All parts are parts by weight unless specifically identified otherwise.

Example 1

[0037] A one liter stainless steel autoclave was charged with 170 grams of washed and dried dicyclopentadiene, 80 grams of washed and dried (+)-limonene and 100 milliliters of xylenes. The reactor was flushed with nitrogen, sealed and heated to 270°C with stirring. The reactor pressure peaked at 185 psig at 270°C. The reactor pressure began to drop as the temperature was maintained at 270°C. Within 15 minutes, the pressure dropped 20 to 30 psig. After one

hour of residence time, the reactor was cooled. The contents were transferred to a flask and heated to 170°C, and the pressure on the surface of the contents was reduced to 25 inches of mercury vacuum. The stripped resin was poured from the flask as molten material at 150°C. A softening point from 55-75°C was determined. The molecular weight range was determined to be 500 to 15,000.

5

Example 2

[0038] The procedures of Example 1 were repeated except the residence time at 270°C was two hours, instead of one hour. The softening point for this polymeric resin ranged from 80 to 131°C. The molecular weight range was determined to be 700 to 15,000.

10

Example 3

[0039] The procedures of Example 1 were repeated, except the residence time at 270°C was 4 hours, and the polymeric resin product had a softening point ranging from 126°C to 168°C. The molecular weight range was determined to be 3,000 to 15,000.

15

Example 4

[0040] The procedures of Example 1 were repeated except the residence time of 270°C was for 6 hours instead of one hour, and the softening point for the resin ranged from 168°C to 195°C. The molecular weight range was determined to be 4,000 to 15,000.

20

Example 5

25

[0041] The dicyclopentadiene/limonene resin from Examples 1-4, were combined by mixing 150 grams of each polymeric resin into a 2-liter stainless steel beaker. A hot plate was used to melt the polymeric resins and stirring gave a homogeneous mixture. The blend was cooled to room temperature, and chipped into small granular pieces, which exhibited an overall softening range of from 78 to 173°C. The product was an amber-color solid.

30

Example 6

[0042] A three liter round bottom flask was fitted with a mechanical stirrer, a constant temperature water bath, a thermocouple and a dropping funnel. The flask was swept with nitrogen and charged with 200 milliliters of cyclohexane containing 10 grams of anhydrous aluminum chloride. Stirring was started and the water bath raised the temperature of the aluminum chloride/cyclohexane suspension to 30°C. The dropping funnel was charged with a 170 grams of dicyclopentadiene that had been washed with 6 percent aqueous sodium hydroxide inhibitor, but not dried after a second washing with water, 80 grams of (+)-limonene of technical grade from Eastman Kodak and 100 milliliters of cyclohexane. The feed stream was added as quickly as possible with the reaction temperature maintained at $32 \pm 2^\circ\text{C}$. After 25 minutes, all of the feed had been added and the reaction temperature of $32 \pm 2^\circ\text{C}$ was maintained for three hours with stirring. A solution of 200 milliliters of isopropanol and 600 milliliters of water was added to the reaction mixture as the heat was removed. The aqueous-organic mixture was stirred vigorously until all of the catalyst had been hydrolyzed. The organic layer which contains a suspended solid was separated and washed with two portions of 200 milliliters of water. The organic layer which contained the suspended solid was dried in a drying oven at 150°C and 28 inches of mercury vacuum. The product softens or shows wetting in a capillary melting point tube at 188 to 208°C with a molecular weight range of 700 to 40,000.

35

40

45

Example 7

[0043] The reaction conditions and procedures of Example 6 were repeated at $42 \pm 2^\circ\text{C}$ to give a resin that softens or shows wetting in a capillary melting tube at 138 to 180°C with a molecular weight range of 700 to 36,000.

50

Example 8

[0044] Reaction conditions and procedures of Example 6 were repeated except the reaction was conducted at $52 \pm 2^\circ\text{C}$ to give a resin that softens or shows wetting in a capillary melting point tube at 134 to 156°C with a molecular weight range of 700 to 24,000.

55

Example 9

[0045] The dicyclopentadiene/limonene resin from Examples 6, 7, and 8 were combined by mixing 75 grams of each polymeric resin into a 2-liter stainless steel beaker. A hot plate was used to liquify the polymeric resins and stirring gave a homogeneous mixture. The blend was cooled to room temperature, and chipped into small granular pieces, which exhibited an overall softening range of from 132°C to 191°C.

Example 10

[0046] Three hundred parts of cyclohexane and 50 parts of anhydrous aluminum chloride were placed into a reactor. While continuously stirring the mixture, 600 parts of a hydrocarbon mixture was slowly added to the reactor over a period of 60 minutes. The hydrocarbon mixture consisted of 30 percent inert hydrocarbons with the remaining 70 percent by weight of the mixture comprising the following resin forming components:

Component	Percent
Limonene	67.0
Dicyclopentadiene	33.0

[0047] The temperature of the reaction was maintained in a range of 25° to 30°C. After an hour of agitation from the time of final addition, the hydrocarbon mixture was added to approximately 4,000 parts of a 25 percent solution of isopropyl alcohol in water to neutralize and decompose the aluminum chloride. The aqueous layer was removed and the resin solution washed with an additional 4,000 parts of the alcohol/water blend.

[0048] The resulting resin solution was steam-distilled at a pot temperature of 235°C. The resulting residual molten resin was cooled to room temperature to provide an 85 percent yield of a hard brittle pale yellow resin having a softening point of 110°C to 129°C. Small molecule GPC analysis gives a molecular weight distribution of 6.7 percent in the 9500 MW range, 69.1 percent in the 1100 MW range, 6.5 percent in the 600 MW range, 9.0 percent in the 450 MW range and 4.6 percent in the 330 MW range.

Example 11

[0049] A rubber stock was prepared which consisted of styrene butadiene rubber and conventional amounts of carbon black antioxidant, sulfur and accelerator, fatty acid and zinc oxide. In addition, each sample contained a highly aromatic processing oil, highly paraffinic process oil and processed soybean oil. In Samples 1 and 3, the three oils were partially replaced with a polymeric dicyclopentadiene/limonene resin. In this study, each of the four polymeric resins prepared in accordance with Examples 1-4 was used at the 6 and 12 phr level (total resin was 24 and 48 phr) and compared with the control compounds. The table below provides the relative amounts of the various oils and resins. In addition, the properties of each of the resulting rubber stocks were tested and are listed in the table. The cured specimens of each rubber stock were prepared by press curing the sample at 150°C for 28 minutes under 280 psi pressure with the exception of those specimens used to test for Streblor, Zwick Rebound, Light Blow Out and DIN Abrasion. The samples for testing for Streblor, Zwick Rebound and Light Blow Out were cured for 38 minutes. The specimens tested for DIN Abrasion were cured for 33 minutes.

Table I

Sample	1	2	3	4
Aromatic Processing Oil	22.00	30.00	14.00	30.00
Paraffinic Processing Oil	22.00	30.00	14.00	30.00
Process Soybean Oil	22.00	30.00	14.00	30.00
Example 1 Resin	6.00		12.00	
Example 2 Resin	6.00		12.00	
Example 3 Resin	6.00		12.00	
Example 4 Resin	6.00		12.00	
Productive Tests:				
Rheometer MDR2000 @ 150°C				
S'Min (dN-m)	2.7	2.4	3.1	2.6
T (1)	5.1	4.7	5.4	5.0
TC25	5.8	5.4	6.3	5.7
TC90	25.5	18.4	32.4	18.1
S'Max (dN-m)	10.0	10.1	10.4	10.5
Delta S' (dN-m)	7.3	7.4	7.2	8.0
S" @ S'Max	2.7	2.1	3.2	2.4
TanD @ S'Max	0.27	0.21	0.31	0.23
Assigned Cures	28	28	28	28

Table I (Cont.)

Sample		1	2	3	4
Stress Strain					
300% Modulus (MPa)		3.2	4.4	3.2	4.8
Tensile (MPa)		7.9	10.0	7.2	7.6
Elongation (%)		684	636	706	468
Rebound					
RT		11.5	12.1	12.7	12.5
100°C		20.8	29.3	17.3	30.0
Hardness					
RT		66.3	59.4	74.7	59.7
100°C		39.1	40.1	44.5	41.3
Streblor Normalized to 0.2"					
Avg Force (N)		105	154	106	N/A
		110	143	121	N/A
Zwick Rebound					
65°C		15.8	20.0	14.2	17.4
95°C		19.0	25.0	14.8	23.8
120°C		22.6	31.0	17.8	30.6
150°C		28.0	37.8	24.2	36.8

Table I (Cont.)

Sample	1	2	3	4
Light Blow Out				
Temp (F)	319	310	362	307
Time (Min)	23	27.5	18	15
DIN Abrasion				
Rating	274	279	282	278
MTS Dynamic Modulus				
E' (MPa)	5.8	5.4	7.0	6.0
Tan Delta	0.45	0.39	0.48	0.40
Autovibron at 60°C				
E' (MPa)	20.8	16.5	40.9	15.1
E" (MPa)	4.2	2.9	6.1	2.5
Tangent Delta	0.19	0.18	0.15	0.17
Autovibron at 100°C				
E' (MPa)	11.8	9.6	17.5	9.0
E" (MPa)	3.2	1.6	3.5	1.4
Tangent Delta	0.19	0.17	0.20	0.16
Autovibron at 150°C				
E' (MPa)	10.4	8.0	14.1	7.5
E" (MPa)	1.8	1.1	2.7	.9
Tangent Delta	0.17	0.13	0.19	0.13

[0050] As one can see from the above data, the effect of using the dicyclopentadiene/limonene resins in place of the aromatic processing oil, paraffinic processing oil and processed soybean oil was to increase the hysteresis (rebound, E", tangent delta) and low strain stiffness (E', hardness) while reducing the cure state (300 percent modulus), cure rate (T25, T90) and tear (Strebler). The dicyclopentadiene/limonene resins gave better storage modulus, loss

modulus and tangent delta throughout the temperature range of 60°C to 150°C. It is this response with temperature that provides enhanced traction and handling.

Example 12

5

[0051] In this example, various resins were evaluated in a rubber compound.

10

[0052] Rubber compositions containing the materials set out in Tables 2 and 3 were prepared in a BR Banbury™ mixer using two separate stages of addition (mixing); namely, one non-productive mix stage and one productive mix stage. The non-productive stage was mixed for 3.5 minutes or to a rubber temperature of 160°C, whichever occurred first. The mixing time for the productive stage was to a rubber temperature of 120°C.

[0053] The rubber compositions are identified herein as Samples 1-3. Samples 1 and 2 are considered herein as controls without the use of the resin used in the present invention being added to the rubber composition. Samples 1 and 2 each contain commercially available resins. Sample 3 is the resin prepared in Example 10.

15

[0054] The samples were cured at 150°C for 28 minutes.

[0055] Table 3 illustrates the behavior and physical properties of the cured Samples 1-3.

20

[0056] Lab data reveals that the new DCPD/Limonene resin in fact enhances the traction and durability properties simultaneously without following the typical tradeoff as previously described. Comparing the dynamic properties from the RPA 2000 and stress-strain data (UTS) of the Coumarone-Indene and phenolic resins, the typical tradeoff of sacrificing durability (lower G' at 40 percent strain, 300 percent modulus and tensile strength) for improved dry traction (increased tan delta and loss compliance at 40 percent strain) is demonstrated. Control A (phenolic resin) is a soft compound with high hysteresis. Control B (Coumarone-Indene resin) is a stiff compound with low hysteresis.

25

[0057] The DCPD/Limonene resin versus the Control A shows that the durability is significantly improved (G' at 40 percent strain, 300 percent modulus and tensile strength) and dry traction is maintained (tan delta and J'' at 40 percent). Control B represents a typical effort to increase the durability of Control A through the use of resins. The DCPD/Limonene resin versus the Control B shows that the durability is only slightly reduced (G' at 40 percent strain, 300 percent modulus and tensile strength) and the dry traction is significantly improved (tan delta and J'' at 40 percent).

30

35

40

45

50

55

Table 2

Samples	Ctrl 1	Ctrl 2	3
Non-Productive			
Emulsion SBR ¹	100	100	100
Carbon Black ²	80.0	80.0	80.0
Aromatic Oil	37.5	37.5	37.5
Stearic Acid	2.0	2.0	2.0
Microcrystalline Wax	2.0	2.0	2.0
Zinc Oxide	3.0	3.0	3.0
Antioxidant ³	1.0	1.0	1.0
Phenolic Resin ⁴	25.0	0	0
Coumarone Indene ⁵ Resin	0	25.0	0
Resin of Example 10	0	0	25.0
Productive			
Accelerators ⁶	3.5	3.5	3.5
Accelerator ⁷	0.25	0.25	0.25
Sulfur	0.95	0.95	0.95

¹ Emulsion SBR containing 40 percent styrene a Tg of 35°C and a base Mooney of 110 when oil extended (37.5 phr oil) the Mooney was 48. The solution SBR was obtained from The Goodyear Tire & Rubber Company.

² I₂=122 and DBP=114

³ Polymerized 1,2-dihydro-2,2,4-trimethylquinoline

⁴ Unreactive phenol-formaldehyde resin having a melting point of 106-114°C (Ring and Ball) which is commercially available from Schenectady Chemical under the designation CRJ-418.

⁵ Coumarone Indene Resin having a softening point of 100°C which is commercially available from Neville Chemical under the designation CumarTM R-13.

⁶ N-cyclohexyl benzothiazole-2-sulfenamide

⁷ Tetramethyl thiuram disulfide

Table 3

Sample	1	2	3
Phenolic resin	25.0	0	0
Coumarone Indene Resin	0	25.0	0
Resin of Example 10	0	0	25.0
RPA 2000, 15.8 min, 160°C, 17% strain, 1.67 Hz			
T25 (min)	1.89	2.98	1.92
T90 (min)	9.3	9.7	9.7
Min Torque (dNm)	0.49	0.59	0.66
Max Torque (dNm)	1.76	2.28	2.28
Delta Torque (dNm)	1.27	1.69	1.62
RPA 2000, 1 Hz, 100°C			
G' 40% (KPa)	376	476	449
Tan Delta 40%	0.254	0.224	0.277
J'' 40% 1/MPa	0.63	0.45	0.57
UTS, cure 28 minutes @ 150°C			
300% Modulus, MPa	3.5	4.1	3.6
Tensile Strength, MPa	13.2	15.8	14.7
Elongation, %	719	718	740
Zwick Rebound, 95°C	29.8	35.6	29.8
Rebound 120°C	35.8	40.6	34

Claims

1. A resin composition characterized by a polymer which is the reaction product of the polymerization reaction between dicyclopentadiene and limonene, said resin having a softening point ranging from 50 to 220°C and a molecular weight ranging from 500 to 42,000 g/mol.
2. A resin composition characterized by comprising a blend of two or more individual resin compositions according to claim 1.
3. A rubber stock characterized by (1) a rubber selected from the group consisting of natural rubber, rubbers derived from a diene monomer or mixtures thereof, and (2) the polymeric resin composition of claim 1 or 2.
4. The rubber stock of claim 3 characterized in that said rubber derived from a diene monomer or mixtures thereof is selected from the group comprising natural rubber, polyisoprene, polybutadiene, polychloroprene, copolymers of isoprene and butadiene, copolymers of styrene and butadiene, copolymers of acrylonitrile and butadiene, copolymers of acrylonitrile and isoprene and blends thereof.
5. The rubber stock of claim 3 characterized in that said polymeric resin composition is present in an amount ranging from 5 to 50 parts per hundred parts of rubber.
6. The rubber stock of claim 5 characterized in that said polymeric resin composition is present in an amount ranging from 10 to 25 parts per hundred parts of rubber.
7. A pneumatic tire having a tread characterized by (1) a rubber selected from the group consisting of natural rubber, rubbers derived from a diene monomer or mixtures thereof, and (2) the polymeric resin composition of claim 1 or 2.

8. The pneumatic tire of claim 7 characterized in that said rubber derived from a diene monomer or mixtures thereof is selected from the group comprising natural rubber, polyisoprene, polybutadiene, polychloroprene, copolymers of isoprene and butadiene, copolymers of styrene and butadiene, copolymers of acrylonitrile and butadiene, copolymers of acrylonitrile and isoprene and blends thereof.

5

9. The pneumatic tire of claim 7 characterized in that said polymeric resin composition is present in an amount ranging from 5 to 50 parts per hundred parts of rubber.

10

10. The pneumatic tire of claim 9 characterized in that said polymeric resin composition is present in an amount ranging from 10 to 25 parts per hundred parts of rubber.

15

20

25

30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 10 1855

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 691 432 A (WILLIAMS THEODORE JOSEPH) 25 November 1997 (1997-11-25) * column 17, line 21; claim 2 *	1	C08F236/20 C08F232/08 C08L21/00
X	DATABASE WPI Section Ch, Week 198709 Derwent Publications Ltd., London, GB; Class A26, AN 1987-062070 XP002136270 & JP 62 018407 A (YASUHARA YUSHI KOGY), 27 January 1987 (1987-01-27) * abstract *	1	
X	US 4 577 006 A (HOLLIS SAMUEL D) 18 March 1986 (1986-03-18) * column 1, line 48; claim 1 *	1	
A	EP 0 249 904 A (MARUZEN PETROCHEM CO LTD) 23 December 1987 (1987-12-23) * claims *	3-10	
A	DATABASE WPI Section Ch, Week 199841 Derwent Publications Ltd., London, GB; Class A18, AN 1998-476848 XP002136271 & JP 10 204216 A (YOKOHAMA RUBBER CO LTD), 4 August 1998 (1998-08-04) * abstract *	3-10	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C08F C08L
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
THE HAGUE		20 Apr11 2000	Van Humbeeck, F
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons</p> <p>&: member of the same patent family, corresponding document</p>			

EPO FORM 1608 03-02 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 10 1855

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

20-04-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5691432 A	25-11-1997	US 5410004 A	25-04-1995
		US 5693731 A	02-12-1997
		CA 2140565 A	25-07-1995
		DE 69508813 D	12-05-1999
		DE 69508813 T	05-08-1999
		EP 0665246 A	02-08-1995
		JP 8048723 A	20-02-1996
JP 62018407 A	27-01-1987	NONE	
US 4577006 A	18-03-1986	EP 0194357 A	17-09-1986
EP 0249904 A	23-12-1987	JP 2517233 B	24-07-1996
		JP 62295933 A	23-12-1987
		DE 3781465 A	08-10-1992
		KR 9604355 B	02-04-1996
		US 4968764 A	06-11-1990
JP 10204216 A	04-08-1998	NONE	

EPO FORM P449

For more details about this annex: see Official Journal of the European Patent Office, No. 12/82